

# CONTACT -> contact@everad-adhesives.com

We look forward to providing you with more information about our latest innovations.

# Everad® TAC 2014 A + 2013 B

Waterborne 2K contact adhesive foam bonding

# **Description**

Everad® TAC 2014 A + TAC 2013 B is a waterborne 2K adhesive. It makes an ideal substitute for solventborne contact adhesives used in the furniture industry.

Delivery form:

Everad<sup>®</sup> TAC 2014 A:

22 kg canister, 120 kg - 240 kg drum, 1 100 kg container.

Everad® TAC 2013 B:

20 kg Cubibox, 21 kg canister, 230 kg drum, 600 kg cubitank,

Everad<sup>®</sup> TAC 2014 A: water-based polymer dispersion. Everad<sup>®</sup> TAC 2013 B: waterborne preparation.

Everad<sup>®</sup> TAC 2014 A: blue. Everad<sup>®</sup> TAC 2013 B: transparent.

# Suggested use

For bonding foam to itself and other substrates, such as wood, textiles and other surfaces (after testing).

Everad® TAC 2014 A + TAC 2013 B has very high tack and has strong cohesion as soon as it dries.

Before using, ensure through testing that the product complies with the expected use.

# **Processing**

# Processing:

Acclimatize all materials before application of the adhesive. Apply adhesive to one or both surfaces, mate and press together. The information is based on tests at a relative air humidity of 65% measured at 20 °C. Values may vary depending on material and working conditions.

# Pre-treatment:

The substrate must be clean and free of dust and grease. Application quantity:

50-150 g/m<sup>2</sup>.

# Application method:

2K low-pressure spray gun (Everad® TAC 2K-2 or similar). All parts in contact with the adhesive must to be of chromium steel or stainless steel (316) or plastic materials. Definitively no coloured metals, aluminium or steel may be used.

# Open time:

Approx. 15 minutes (depending on the quantity of adhesive). Mixing ratio:

100: 15/25 according application.

Dilution:

Product is ready for use.

Press method:

A firm pressing operation on the substrates increases the final bond strength.

Final strength:

High initial strength. The ultimate strength is achieved after 48

# Chemical and physical properties in liquid form

Everad® TAC 2014 A: Approx. 1.11 g/cm3.

Viscosity:
Everad® TAC 2014 A : Approx. 75 mPa·s (Brookfield B2V100). Viscosity measured after production. Values may fluctuate up or down during the storage of the product.

Everad<sup>®</sup> TAC 2014 A: 12.0. Everad<sup>®</sup> TAC 2013 B: 2.3.

Minimum application temperature:

15-25°C

Flammability:

As aqueous adhesive, non-flammable.

**VOC** content:

0%

Frost resistance:

Frost sensitive.

#### Film properties

Surface:

Not tacky. Softness:

Very soft.

Liquid adhesive with Everad® TAC Washer. Dried adhesive with Everad® TAC Detergent 2.

# Working safety

Please follow instructions on the safety data sheet. There is no legal requirement of precautionary measures. To avoid the risk of allergy, it is advisable to work with gloves or protect hands with barrier cream. For spray application, we recommend wearing masks and working under an air extractor

# **Storage**

Everad® TAC 2014 A 6 months and Everad® TAC 2013 B 12 months, cool and dry in unopened original packaging, after production.

We guarantee the consistency and faultless quality of this product, manufactured in we guarantee in Consistency and radiums squainty of this product, internatured in accordance with ISO quality standards, which has been developed on the basis of our long-standing experience with the recommended applications under the specified conditions. Material, processing, and application conditions may significantly influence product properties. Pre-application tests by the user are therefore essential. For non-specified applications or deviations in application conditions, we recommend that our technical support service be consulted first. Our general sales and delivery terms and conditions shall apply.