

CONTACT -> contact@everad-adhesives.com

We look forward to providing you with more information about our latest innovations.

Everad® RXB 8801 A+B

Technical 2 component PUR resin

Description

Everad® RXB 8801 A+B is a 2 component polyurethane adhesive. This product does not contain any solvent, phthalate or halogen components.

Packaging:

A: Container 1 000 kg.

B: drum 250 kg.

Base:

Polyol/Polyurethane.

Usage

Everad® RXB 8801 A+B is designed to manufacture of electric and electronic components such as low voltage transformers. Many other uses are possible after preliminary tests.

Before any industrial use, to ensure itself by tests which the product corresponds well to the desired use.

Application

Preparation:

The parts to be glued have to be dry, clean and not dusty. If needed, apply an adapted primer. The two components of the adhesive are adapted one to the other. Stir up component A before mixing it the other and add the component B homogeneously.

The treatment is done with a spatula with teeth or a mixer and batcher. Check regularly the good performance of the dosing-mixing units. Respect the instructions of the manufacturer.

Application temperature:

Min. +10°C.

Application:

Dosing-mixing machine, spatula.

Application quantity:

From 1-2 g to 1 kg depending of the volume to fill.

Pot-life:

Approx. 9 minutes at 25°C for 200 g. The value depends of the substrates to assembly, environmental conditions and the used process.

Chemical and physical properties

Solid content:

ca. 100%

Viscosity:

A: approx. 8 000 mPa.s at 25°C (Brookfield B4V20).

B: approx. 150 mPa.s at 25°C (Brookfield B2V100).

Mix: approx. 3 400 mPa.s at 25°C (Brookfield B4V20).

Viscosity measured after production. Values may fluctuate up or down during the storage of the product.

Density:A: approx. 1,59 g/cm³ at 20°C.B: approx. 1.2 g/cm³ at 20°C.Mix: approx. 1.48 g/cm³ at 20°C.**Mixing ratio:**

A:B : 100:40 (in weight)

A:B : 100:52 (in volume)

Flammability:

Non flammable.

Shore:

90 D/1

Resistance

Rupture module:

60 MPa (ISO 527).

Rupture elongation:

3%. (ISO 527).

Temperature resistance:

-40°C to +150°C.

Dielectric properties

Dielectric rigidity:14 K_Veff/mm (CEI 60243-1)**Relative permittivity:**

4.9 (50 Hz) (CEI 60250)

Tan delta:

0.02 (50Hz) 5CEI 60250)

Clean-up

Everad® RXB 8801 A+B liquid with Everad® SNE 3739.

Everad® RXB 8801 A+B reticulated with

Everad® RPS Solvant 4.

Protection of the metallic parts soiled by

Everad® RSB 8801 A+B by soaking in Everad® HNE D-Col 12.

Rinse of the mixing head with Everad® RPS Solvant 3.

Safety

The wearing of protective gloves and safety goggles is recommended while handling the liquid product. Please follow the instructions on the Safety Data Sheet.

Storage

Protect from humidity.

Cool and dry, storage between 15 and 25°C, in unopened original packaging 6 months after production (Comp. A) and 12 months after production (Comp. B).

Guarantee

We guarantee the consistency and faultless quality of this product, manufactured in accordance with ISO quality standards, which has been developed on the basis of our long-standing experience with the recommended applications under the specified conditions. Material, processing, and application conditions may significantly influence product properties. Pre-application tests by the user are therefore essential. For non-specified applications or deviations in application conditions, we recommend that our technical support service be consulted first. Our general sales and delivery terms and conditions shall apply.